
DATA SHEET

Product Number: 399-10-164-10-008000



Description:

Interconnect Header Spring-Loaded Target Connector Right Angle Mount Single Row Through Hole

Plating Code:

10

Shell Plating:

 $10~\mu$ " Gold over $100~\mu$ " Nickel

# Of Pins	Mill-Max Part Number	RoHS Compliant
		_

64

399-10-164-10-008000



LOOSE PIN:

Pin Used: 1940 (Brass Alloy)

BRASS ALLOY (UNS C36000) per ASTM B 16

Properties of BRASS ALLOY:

- Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†
- Hardness as machined: 80-90 Rockwell B
- Density: .307 lbs/in3
- Electrical conductivity: 26% IACS*
- Melting point: 900°C/885°C (liquidus/solidus)

†(3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

INSULATOR INFORMATION:

^{*}International Annealed Copper Standard, i.e. as a % of pure copper.

PCT Polyester, (Thermx CG933, black)

High Temperature

Properties of PCT Polyester:

- Brand: Thermx • Grade: CG-933

- Rated voltage: 100 VRMS/150 VDC
 Insulation resistance: 10,000 Megaohms min.
 Material Heat Deflection Temp (per ASTM D 648): 529°F (276°C) @ 66 psi
 Dielectric strength: 1000 VRMS min. (700 VRMS min. for series 117 Shrink DIP)

Note: Materials above 446°F (230°C) are considered suitable for "eutectic" reflow soldering, above $500^{\circ}F$ (260°C) for "lead-free" reflow soldering.